



Silocord ® / Alim Abras



ility hose

VC-granulate, grains and food. Static grounding the static wire.

ding to the right standards:

t. 4 FDA (CFR 21 § 177. 2600)

Felirat: ® SILOCORD® / ALIM GRANULATE PN 8 BAR - BfR XXI KAT. 4 - FDA

Operating pressure: 8 bar

Bursting pressure: 24 bar

Heat resistance: -30°C/+80°C

Intterior: NR/SBR, white, smooth, anrasion resistant, food quality

Exterior: SBR, black, fabric imprinted

Linings: fabrid lining and two crossed steel wire helix

Abrasion resistance: 100 - 110mm3 according to ISO 4649 (earlier DIN 53516) standard

Storage lots, splitting of the rolls are possible. Meantime, we hold the right of selling the stock in products.

Inside Ø (mm)	Wall thickness (mm)	Outside Ø (mm)	Roll size (m)	Article number
75	9	93	40	3560 075000
100	10	120	40	3560 100000